



TEST REPORT

Report No.: CCI260600497EN

Report Date: Jun. 29, 2026

Page 1 of 14

Applicant : Mid Ocean Brands B.V.

Address : Unit 711-716, 7/F., Tower A, 83 King Lam Street Cheung Sha Wan, Kowloon, Hong Kong

(The following sample(s) was (were) submitted and identified by client as)

Sample Name : RPET bottle

Model/Item No. : MO9910

Vendor Code : 107978

Test Period : From May 22, 2026 to Jun. 29, 2026

Tests Conducted : As requested by the applicant, for details refer to next page(s).

Signed for and on behalf of

Compliance Control Institute (Guangzhou) Co., Ltd.

Approved by: _____

Pascal SHI/Technical Director

Compliance Control Institute (Guangzhou) Co., Ltd.

Room 701, Building 2, No.89, Majun Street, Nansha District, Guangzhou,
Guangdong, China
Tel: +86-20-84900678 Fax: +86-20-84910993
Email: cs@ccilab.com.cn Website: www.ccilab.com.cn

This report is governed by, and incorporates by reference, the General Terms and Conditions of Testing which could be obtained / consulted by request to CCI or via the webpage of Conditions of Testing in the official website: www.ccilab.com.cn. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. This report sets forth our findings solely respect to the client's request(s) and the test results are obtained just with the submitted sample identified herein. The test results set forth in this report are not indicative or representative of the quality or characteristics of the lot from which a test sample was taken or any similar or identical product unless specifically and expressly noted. This report can not be reproduced except in full, without prior written permission of CCI. Any unauthorized alteration, forgery or falsification of the content or appearance of this report is unlawful, and any offenders may be prosecuted to the fullest extent of the law.



TEST REPORT

Report No.: CCI260600497EN

Report Date: Jun. 29, 2026

Page 2 of 14

Executive Summary:

No.	TESTED SAMPLES	STANDARD / REQUIREMENT	CONCLUSION
1	Tested material(s) of submitted sample(s)	Entry 23 of Annex XVII to the REACH Regulation (EC) No.1907/2006 - Cadmium (Cd)	PASS
2	Tested material(s) of submitted sample(s)	Entry 43 of Annex XVII to the REACH Regulation (EC) No.1907/2006 – Azo colorants and Azo dyes	PASS
3	Tested material(s) of submitted sample(s)	Entry 50 of Annex XVII to the REACH Regulation (EC) No.1907/2006 - Polycyclic-aromatic hydrocarbons (PAH)	PASS
4	Tested material(s) of submitted sample(s)	Entry 51&52 of Annex XVII to the REACH Regulation (EC) No.1907/2006 - Phthalate	PASS
5	Tested material(s) of submitted sample(s)	Entry 63 of Annex XVII to the REACH Regulation (EC) No.1907/2006 - Lead (Pb)	PASS
6	Tested material(s) of submitted sample(s)	Client's requirements on Colour fastness to rubbing	PASS
7	Tested material(s) of submitted sample(s)	Regulation (EC) No. 1935/2004 & Regulation (EU) No 10/2011 and amendment directive (EU) 2020/1245 and the amendment Commission Regulation (EU) 2024/3190 for plastic materials - Overall Migration - 3% Acetic acid - 50% Ethanol - Specific migration of restricted substances - Specific migration of Primary Aromatic Amines - Bisphenol A (BPA)	PASS
8	Tested material(s) of submitted sample(s)	Regulation (EC) No. 1935/2004 & Resolution AP(2004)5 on Silicone rubber products intended to come into contact with foodstuffs - Overall Migration - 3% Acetic acid - 50% Ethanol - Bisphenol A (BPA)	PASS
9	Tested material(s) of submitted sample(s)	French Arrêté du 25 novembre 1992 on Silicon - Overall Migration - 3% Acetic acid - 50% Ethanol - Volatile Organic matter (VOM) - Peroxide Value - Specific migration of organotin (As Tin) - Bisphenol A (BPA)	PASS



TEST REPORT

Report No.: CCI260600497EN

Report Date: Jun. 29, 2026

Page 3 of 14

TESTS CONDUCTED:

1. Cadmium (Cd)

Test Method: With reference to EPA 3052:1996, EPA 3050B:1996, the analysis was performed by Atomic Absorption Spectroscopy (AAS) or Inductively Coupled Plasma Optical Emission Spectrometer (ICP-OES).

Material No.	Limit (mg/kg)	RL (mg/kg)	Test Result (mg/kg)	Conclusion
2+5+7	100	2	N.D.	PASS
6	100	2	N.D.	PASS

Note:

1. mg/kg = Milligram per kilogram.
2. N.D. = Not Detected (< RL).
3. RL = Reporting Limit.

2. Azo colorants and Azo dyes

Test Method: With reference to EN ISO 14362-1:2017, by Gas Chromatography-Mass Spectrometry (GC-MS) analysis.

No.	ANALYTE	CAS No.	RL (mg/kg)	Limit (mg/kg)	Test Result (mg/kg)
					1+3
1	4-aminodiphenyl	92-67-1	5	30	N.D.
2	Benzidine	92-87-5	5	30	N.D.
3	4-chloro-o-toluidine	95-69-2	5	30	N.D.
4	2-naphthylamine	91-59-8	5	30	N.D.
5	o-aminoazotoluene	97-56-3	5	30	N.D.
6	2-amino-4-nitrotoluene	99-55-8	5	30	N.D.
7	p-chloroaniline	106-47-8	5	30	N.D.
8	2,4-diaminoanisole	615-05-4	5	30	N.D.
9	4,4'-diaminodiphenylmethane	101-77-9	5	30	N.D.
10	3,3'-dichlorobenzidine	91-94-1	5	30	N.D.
11	3,3'-dimethoxybenzidine	119-90-4	5	30	N.D.
12	3,3'-dimethylbenzidine	119-93-7	5	30	N.D.
13	3,3'-dimethyl-4,4'-diaminodiphenylmethane	838-88-0	5	30	N.D.
14	p-cresidine	120-71-8	5	30	N.D.
15	4,4'-methylene-bis-(2-chloroaniline)	101-14-4	5	30	N.D.

Compliance Control Institute (Guangzhou) Co., Ltd.

Room 701, Building 2, No.89, Majun Street, Nansha District, Guangzhou, Guangdong, China
Tel: +86-20-84900678 Fax: +86-20-84910993
Email: cs@ccilab.com.cn Website: www.ccilab.com.cn

This report is governed by, and incorporates by reference, the General Terms and Conditions of Testing which could be obtained / consulted by request to CCI or via the webpage of Conditions of Testing in the official website: www.ccilab.com.cn. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. This report sets forth our findings solely respect to the client's request(s) and the test results are obtained just with the submitted sample identified herein. The test results set forth in this report are not indicative or representative of the quality or characteristics of the lot from which a test sample was taken or any similar or identical product unless specifically and expressly noted. This report can not be reproduced except in full, without prior written permission of CCI. Any unauthorized alteration, forgery or falsification of the content or appearance of this report is unlawful, and any offenders may be prosecuted to the fullest extent of the law.



TEST REPORT

Report No.: CCI260600497EN

Report Date: Jun. 29, 2026

Page 4 of 14

No.	ANALYTE	CAS No.	RL (mg/kg)	Limit (mg/kg)	Test Result (mg/kg)
					1+3
16	4,4'-oxydianiline	101-80-4	5	30	N.D.
17	4,4'-thiodianiline	139-65-1	5	30	N.D.
18	o-toluidine	95-53-4	5	30	N.D.
19	2,4-diaminotoluene	95-80-7	5	30	N.D.
20	2,4,5-trimethylaniline	137-17-7	5	30	N.D.
21	2-methoxyaniline	90-04-0	5	30	N.D.
22	4-aminoazobenzene *	60-09-3	5	30	N.D.
Conclusion					PASS

Note:

1. RL= Reporting Limit.
2. mg/kg = Milligram per kilogram.
3. N.D. = Not Detected (< RL).
4. * = Azo colorants that are able to form 4-aminoazobenzene, generate aniline and 1,4-phenylenediamine under the condition of test method EN ISO 14362-1:2017, The presence of these colorants can not be confirmed by this test method. The result of 4-aminoazobenzene is analysed and confirmed by test method EN ISO 14362-3:2017.
5. For the tested samples in this report, the aniline and 1,4-phenylenediamine were not found.

3. Polycyclic-aromatic hydrocarbons (PAH)

Test Method: With reference to AfPS GS 2019:01 PAK, the analysis was performed by Gas Chromatography-Mass Spectrometry (GC-MS).

Restricted Substances	CAS No.	RL (mg/kg)	Test Result (mg/kg)	
			2+5+7	6
Benzo[a]pyrene (BaP)	50-32-8	0.2	N.D.	N.D.
Benzo[e]pyrene (BeP)	192-97-2	0.2	N.D.	N.D.
Benzo[a]anthracene (BaA)	56-55-3	0.2	N.D.	N.D.
Chrysen (CHR)	218-01-9	0.2	N.D.	N.D.
Benzo[b]fluoranthene (BbFA)	205-99-2	0.2	N.D.	N.D.
Benzo[j]fluoranthene (BjFA)	205-82-3	0.2	N.D.	N.D.
Benzo[k]fluoranthene (BkFA)	207-08-9	0.2	N.D.	N.D.
Dibenzo[a,h]anthracene (DBAhA)	53-70-3	0.2	N.D.	N.D.
Conclusion			PASS	PASS



TEST REPORT

Report No.: CCI260600497EN

Report Date: Jun. 29, 2026

Page 5 of 14

Note:

1. mg/kg = Milligram per kilogram.
2. N.D. = Not Detected (< RL).
3. RL = Reporting Limit.
4. Requirement: a) For articles for supply to the general public: No more than 1mg/kg each;
b) For toys: No more than 0.5mg/kg each.

4. Phthalates

Test Method: With reference to EN 14372:2004, the analysis was performed by Gas Chromatography-Mass Spectrometry (GC-MS).

Restricted Substances	CAS No.	RL (%)	Limit (%)	Test Result (%)	
				2+5+7	6
Bis(2-ethylhexyl) phthalate (DEHP)	117-81-7	0.003	0.1	N.D.	N.D.
Dibutyl phthalate (DBP)	84-74-2	0.003	0.1	N.D.	N.D.
Benzyl butyl phthalate (BBP)	85-68-7	0.003	0.1	N.D.	N.D.
Diisobutyl phthalate (DIBP)	84-69-5	0.003	0.1	N.D.	N.D.
Sum		/	0.1	N.D.	N.D.
Di-isononyl phthalate (DINP)	28553-12-0 68515-48-0	0.005	0.1	N.D.	N.D.
Di-isodecyl phthalate (DIDP)	26761-40-0 68515-49-1	0.005	0.1	N.D.	N.D.
Di-n-octyl phthalate (DNOP)	117-84-0	0.003	0.1	N.D.	N.D.
Sum		/	0.1	N.D.	N.D.
Conclusion				PASS	PASS

Note:

1. % = Percentage by weight.
2. N.D. = Not Detected (< RL).
3. RL = Reporting Limit.
4. / = Not Specified.



TEST REPORT

Report No.: CCI260600497EN

Report Date: Jun. 29, 2026

Page 6 of 14

5. Lead (Pb)

Test Method: With reference to EPA 3052:1996, EPA 3050B:1996, the analysis was performed by Atomic Absorption Spectroscopy (AAS) or Inductively Coupled Plasma Optical Emission Spectrometer (ICP-OES).

Material No.	Limit (mg/kg)	RL (mg/kg)	Test Result (mg/kg)	Conclusion
1+3	500	2	N.D.	PASS
2+5+7	500	2	N.D.	PASS
4	500	2	N.D.	PASS
6	500	2	N.D.	PASS

Note:

1. mg/kg = Milligram per kilogram.
2. N.D. = Not Detected (< RL).
3. RL = Reporting Limit.

6. Colour fastness to rubbing

Test method: ISO 105-X12:2016(E).

Material No.	Test Item	Client's Limit (Grade)	Results (Grade)	Conclusion
1	Dry (Colour Staining)	2-3	4-5	PASS
	Wet (Colour Staining)	2-3	4-5	PASS
3	Dry (Colour Staining)	2-3	4-5	PASS
	Wet (Colour Staining)	2-3	4-5	PASS

Note:

Explanation of Colour fastness Results

- Grade 5 Negligible or no change or staining
Grade 4 Slightly changed or stained
Grade 3 Noticeably changed or stained
Grade 2 Considerably changed or stained
Grade 1 Much changed or heavily stained



TEST REPORT

Report No.: CCI260600497EN

Report Date: Jun. 29, 2026

Page 7 of 14

7.1. Overall Migration

Test Method: With reference to EN 1186-1:2002, EN 1186-3:2022

Material No. 5 : S/V ration: 1.38 dm² / 138 mL

Material No. 7 : S/V ration: 3.99 dm² / 572 mL

Simulant Used	Limit (mg/dm ²)	RL (mg/dm ²)	Test Result (mg/dm ²)	
			5	7
Overall Migration - 3% Acetic acid (40°C, 10 D)	10	1	N.D.	N.D.
Overall Migration - 50% Ethanol (40°C, 10 D)	10	1	N.D.	N.D.
Conclusion			PASS	PASS

Note:

1. mg/dm² = Milligram per square decimeter.
2. N.D. = Not Detected (< RL).
3. RL = Reporting Limit.



TEST REPORT

Report No.: CCI260600497EN

Report Date: Jun. 29, 2026

Page 8 of 14

7.2. Specific migration of restricted substances

Test Method: EN 13130-1:2004, the analysis was performed by Inductively Coupled Plasma Mass Spectrometer (ICP-MS) or Inductively Coupled Plasma-Optical Emission Spectrometer (ICP-OES).

Test Condition: 3% acetic acid, 40°C, 10D

Material No. 5 : S/V ration: 1.38 dm² / 230 mL

Material No. 7 : S/V ration: 3.99 dm² / 572 mL

Test Item	Limit (mg/kg)	RL (mg/kg)	Test Result (mg/kg)	
			5	7
Aluminum (Al)	1	0.05	N.D.	N.D.
Manganese (Mn)	0.6	0.05	N.D.	N.D.
Iron (Fe)	48	0.05	N.D.	N.D.
Cobalt (Co)	0.05	0.01	N.D.	N.D.
Copper (Cu)	5	0.05	N.D.	N.D.
Zinc (Zn)	5	0.1	N.D.	N.D.
Barium (Ba)	1	0.05	N.D.	N.D.
Nickel (Ni)	0.02	0.01	N.D.	N.D.
Lithium (Li)	0.6	0.02	N.D.	N.D.
Antimony (Sb)	0.04	0.01	N.D.	N.D.
Arsenic (As)	N.D.	0.01	N.D.	N.D.
Cadmium (Cd)	N.D.	0.002	N.D.	N.D.
Calcium (Ca)	/	0.01	N.D.	N.D.
Chromium (Cr)	N.D.	0.01	N.D.	N.D.
Europium (Eu)	0.05	0.05	N.D.	N.D.
Gadolinium (Gd)	0.05	0.05	N.D.	N.D.
Lanthanum (La)	0.05	0.05	N.D.	N.D.
Lead (Pb)	N.D.	0.01	N.D.	N.D.
Magnesium (Mg)	/	0.01	N.D.	N.D.
Mercury (Hg)	N.D.	0.01	N.D.	N.D.
Potassium (K)	/	0.01	N.D.	N.D.
Sodium (Na)	/	0.01	N.D.	N.D.
Terbium (Tb)	0.05	0.05	N.D.	N.D.
Conclusion			PASS	PASS

Note:

1. mg/kg = Milligram per kilogram.

2. N.D. = Not Detected (< RL).

3. RL = Reporting Limit.

Compliance Control Institute (Guangzhou) Co., Ltd.

Room 701, Building 2, No.89, Majun Street, Nansha District, Guangzhou, Guangdong, China
Tel: +86-20-84900678 Fax: +86-20-84910993
Email: cs@ccilab.com.cn Website: www.ccilab.com.cn

This report is governed by, and incorporates by reference, the General Terms and Conditions of Testing which could be obtained / consulted by request to CCI or via the webpage of Conditions of Testing in the official website: www.ccilab.com.cn. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. This report sets forth our findings solely respect to the client's request(s) and the test results are obtained just with the submitted sample identified herein. The test results set forth in this report are not indicative or representative of the quality or characteristics of the lot from which a test sample was taken or any similar or identical product unless specifically and expressly noted. This report can not be reproduced except in full, without prior written permission of CCI. Any unauthorized alteration, forgery or falsification of the content or appearance of this report is unlawful, and any offenders may be prosecuted to the fullest extent of the law.



TEST REPORT

Report No.: CCI260600497EN

Report Date: Jun. 29, 2026

Page 9 of 14

7.3. Specific migration of Primary Aromatic Amines Test Method: With reference to EN 13130-1:2004

Test Condition: 3% acetic acid, 40°C, 10D

Material No. 5 : S/V ratio: 1.38 dm² / 230 mL

Material No. 7 : S/V ratio: 3.99 dm² / 572 mL

No.	Test Item	CAS No.	Limit (mg/kg)	RL (mg/kg)	Test Result (mg/kg)	
					5	7
1	4-aminodiphenyl	92-67-1	N.D.	0.002	N.D.	N.D.
2	Benzidine	92-87-5	N.D.	0.002	N.D.	N.D.
3	4-chloro-o-toluidine	95-69-2	N.D.	0.002	N.D.	N.D.
4	2-naphthylamine	91-59-8	N.D.	0.002	N.D.	N.D.
5	o-aminoazotoluene	97-56-3	N.D.	0.002	N.D.	N.D.
6	2-amino-4-nitrotoluene	99-55-8	N.D.	0.002	N.D.	N.D.
7	p-chloroaniline	106-47-8	N.D.	0.002	N.D.	N.D.
8	2,4-diaminoanisole	615-05-4	N.D.	0.002	N.D.	N.D.
9	4,4,-diaminodiphenylmethane	101-77-9	N.D.	0.002	N.D.	N.D.
10	3,3,-dichlorobenzidine	91-94-1	N.D.	0.002	N.D.	N.D.
11	3,3,-dimethoxybenzidine	119-90-4	N.D.	0.002	N.D.	N.D.
12	3,3,-dimethylbenzidine	119-93-7	N.D.	0.002	N.D.	N.D.
13	3,3,-dimethyl- 4,4,diaminodiphenylmethane	838-88-0	N.D.	0.002	N.D.	N.D.
14	p-cresidine	120-71-8	N.D.	0.002	N.D.	N.D.
15	4,4,-methylene-bis-(2-chloroaniline)	101-14-4	N.D.	0.002	N.D.	N.D.
16	4,4,-oxydianiline	101-80-4	N.D.	0.002	N.D.	N.D.
17	4,4,-thiodianiline	139-65-1	N.D.	0.002	N.D.	N.D.
18	o-toluidine	95-53-4	N.D.	0.002	N.D.	N.D.
19	2,4-diaminotoluene	95-80-7	N.D.	0.002	N.D.	N.D.
20	2,4,5-trimethylaniline	137-17-7	N.D.	0.002	N.D.	N.D.
21	2-methoxyaniline	90-04-0	N.D.	0.002	N.D.	N.D.
22	4-aminoazobenzene	60-09-3	N.D.	0.002	N.D.	N.D.
Other primary aromatic amines (sum)			0.01	/	N.D.	N.D.
23	1,4-Phenylenediamine	106-50-3	/	0.002	N.D.	N.D.
24	1,3-Phenylenediamine	108-45-2	/	0.002	N.D.	N.D.
25	Aniline	62-53-3	/	0.002	N.D.	N.D.
26	2,6-Dimethylaniline (2,6-DMA)	87-62-7	/	0.002	N.D.	N.D.
27	2,4'-Diaminodiphenylmethane	1208-52-2	/	0.002	N.D.	N.D.
28	2,4-Dimethylaniline (2,4-DMA)	95-68-1	/	0.002	N.D.	N.D.



TEST REPORT

Report No.: CCI260600497EN

Report Date: Jun. 29, 2026

Page 10 of 14

29	2,2'-Methylenedianiline	6582-52-1	/	0.002	N.D.	N.D.
Conclusion					PASS	PASS

Note:

1. mg/kg = Milligram per kilogram.
2. N.D. = Not Detected (< RL).
3. RL = Reporting Limit.

7.4. Bisphenol A (BPA)

Test Method: With reference to EPA 3550C:2007, the analysis was performed by Ultra High Performance Liquid Chromatography coupled with tandem Mass Spectrometry (UPLC-MS-MS).

Material No.	Limit (µg/kg)	RL (µg/kg)	Test Result (µg/kg)	Conclusion
5	Not Detected	1	N.D.	PASS
7	Not Detected	1	N.D.	PASS

Note:

1. µg/kg = Microgram per kilogram.
2. N.D. = Not Detected (< RL).
3. RL = Reporting Limit.

8.1. Overall Migration

Test Method: With reference to EN 1186-1:2002, EN 1186-3:2022

S/V ration: 1.08 dm² / 108 mL

Simulant Used	Limit (mg/dm ²)	RL (mg/dm ²)	Test Result (mg/dm ²)
			6
Overall Migration - 3% Acetic acid (40°C, 10 D)	10	1	N.D.
Overall Migration - 50% Ethanol (40°C, 10 D)	10	1	N.D.
Conclusion			PASS

Note:

1. mg/dm² = Milligram per square decimeter.
2. N.D. = Not Detected (< RL).
3. RL = Reporting Limit.



TEST REPORT

Report No.: CCI260600497EN

Report Date: Jun. 29, 2026

Page 11 of 14

8.2. Bisphenol A (BPA)

Test Method: With reference to EPA 3550C:2007, the analysis was performed by Ultra High Performance Liquid Chromatography coupled with tandem Mass Spectrometry (UPLC-MS-MS).

Material No.	Limit (µg/kg)	RL (µg/kg)	Test Result (µg/kg)	Conclusion
6	Not Detected	1	N.D.	PASS

Note:

1. µg/kg = Microgram per kilogram.
2. N.D. = Not Detected (< RL).
3. RL = Reporting Limit.

9.1. Overall Migration

Test Method: With reference to the Annex III to Arrêté du 25 novembre 1992

S/V ration: 1.08 dm² / 108 mL

Simulant Used	Limit (mg/dm ²)	RL (mg/dm ²)	Test Result (mg/dm ²)		
			6		
Overall Migration - 3% Acetic acid (40°C, 10D)	10	1	N.D.	N.D.	N.D.
Overall Migration - 50% Ethanol (40°C, 10D)	10	1	N.D.	N.D.	N.D.
Conclusion			PASS		

Note:

1. mg/dm² = Milligram per square decimeter.
2. N.D. = Not Detected (< RL).
3. RL = Reporting Limit.

9.2. Volatile organic matter (VOM)

Test Method: With reference to the Annex III to Arrêté du 25 novembre 1992

Test Condition: 200°C, 4h

Material No.	Limit (%)	RL (%)	Test Result (%)	Conclusion
6	0.5	0.1	0.2	PASS

Note:

1. % = Percentage by weight.
2. N.D. = Not Detected (< RL).
3. RL = Reporting Limit.

Compliance Control Institute (Guangzhou) Co., Ltd.

Room 701, Building 2, No.89, Majun Street, Nansha District, Guangzhou, Guangdong, China
Tel: +86-20-84900678 Fax: +86-20-84910993
Email: cs@ccilab.com.cn Website: www.ccilab.com.cn

This report is governed by, and incorporates by reference, the General Terms and Conditions of Testing which could be obtained / consulted by request to CCI or via the webpage of Conditions of Testing in the official website: www.ccilab.com.cn. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues identified therein. This report sets forth our findings solely respect to the client's request(s) and the test results are obtained just with the submitted sample identified herein. The test results set forth in this report are not indicative or representative of the quality or characteristics of the lot from which a test sample was taken or any similar or identical product unless specifically and expressly noted. This report can not be reproduced except in full, without prior written permission of CCI. Any unauthorized alteration, forgery or falsification of the content or appearance of this report is unlawful, and any offenders may be prosecuted to the fullest extent of the law.



TEST REPORT

Report No.: CCI260600497EN

Report Date: Jun. 29, 2026

Page 12 of 14

9.3. Peroxide Value

Test Method: With reference to the French pharmacopeia, 9th edition

Material No.	Limit	Test Result	Conclusion
6	Negative	Negative	PASS

9.4. Specific migration of organotin (As Tin)

Test Method: With reference to Kunststoffe im Lebensmittelverkehr, Part B II IX

Test Item	Limit (mg/kg)	RL (mg/kg)	Test Result (mg/kg)
			6
Tin	0.1	0.1	N.D.
Conclusion			PASS

Note:

1. mg/kg = Milligram per kilogram.
2. N.D. = Not Detected (< RL).
3. RL = Reporting Limit.

9.5. Bisphenol A (BPA)

Test Method: With reference to EPA 3550C:2007, the analysis was performed by Ultra High Performance Liquid Chromatography coupled with tandem Mass Spectrometry (UPLC-MS-MS).

Material No.	Limit (µg/kg)	RL (µg/kg)	Test Result (µg/kg)	Conclusion
6	Not Detected	1	N.D.	PASS

Note:

1. µg/kg = Microgram per kilogram.
2. N.D. = Not Detected (< RL).
3. RL = Reporting Limit.



TEST REPORT

Report No.: CCI260600497EN

Report Date: Jun. 29, 2026

Page 13 of 14

Test Material(s) List

Material No.	Description	Location	Material
1	Gray fabric	Handle	/
2	Black plastic	Joint	/
3	Gray textile	String	/
4	Silvery metal	Outer cover	/
5	Gray plastic	Inner cover	PP
6	Translucent silicone	Sealing ring	Silicone
7	Transparent black plastic	Bottle body	RPET




TEST REPORT

Report No.: CCI260600497EN

Report Date: Jun. 29, 2026

Page 14 of 14

Photo Appendix



Additional Photo Appendix



★★★★★End of Report★★★★★