



中国认可  
国际互认  
检测  
TESTING  
CNAS L6478



# TEST REPORT

**Report No.**..... : WTF22F09192785C  
**Applicant**..... : Mid Ocean Brands B.V.  
**Address**..... : 7/F., Kings Tower, 111 King Lam Street, Cheung Sha Wan, Kowloon, Hong Kong  
**Manufacturer**..... : 109979  
**Sample Name**..... : Round Magnetic Wireless charger, Bamboo Magnetic Wireless charger, Magnetic wireless charger with stand  
**Sample Model**..... : MO6253, MO6266, MO6369  
**Date of Receipt sample**..... : 2022-09-22  
**Testing period**..... : 2022-09-22 to 2022-11-02  
**Date of Issue**..... : 2022-11-03  
**Test Result**..... : Refer to next page (s)

**Prepared By:**

**Waltek Testing Group (Foshan) Co., Ltd.**

Address: No.13-19, 2/F., 2nd Building, Sunlink International Machinery City, Chencun, Shunde District, Foshan, Guangdong, China

Tel:+86-757-23811398 Fax:+86-757-23811381 E-mail:info@waltek.com.cn

Signed for and on behalf of  
Waltek Testing Group (Foshan) Co., Ltd.

Swing.Liang



Report No.: WTF22F09192785C

- Test Requested** ..... : In accordance with the RoHS Directive 2011/65/EU and its amendment (EU) No. 2015/863.
- Test Method**..... : 1) With reference to IEC 62321-2:2021, disassembly, disjunction and mechanical sample preparation  
2) With reference to IEC 62321-3-1:2013, screening - Lead, mercury, cadmium, total chromium and total bromine by X-ray fluorescence spectrometry  
3) With reference to IEC 62321-4:2013+AMD1:2017 CSV, determination of Mercury by ICP-OES  
4) With reference to IEC 62321-5:2013, determination of Lead and Cadmium by ICP-OES  
5) With reference to IEC 62321-7-2: 2017 and IEC 62321-7-1: 2015, determination of Hexavalent Chromium by UV-Vis  
6) With reference to IEC 62321-6:2015, determination of PBBs and PBDEs by GC-MS  
7) With reference to IEC 62321-8:2017, determination of Phthalates content by GC-MS.
- Test Conclusion** ..... : **Pass** (Based on the performed tests on the submitted samples, the results comply with the RoHS Directive 2011/65/EU and its amendment (EU) No. 2015/863)

# WALTEK



Sample Photo(s):



1.MO 6369




Split parts



2.MO 6266



3.MO 6253



Split parts



/

**Test Results:****1. Lead, Mercury, Cadmium, Hexavalent Chromium, PBBs and PBDEs**

Part No.	Part Description	Result of XRF					Result of Wet Chemical Testing (mg/kg)
		Cd	Pb	Hg	Cr	Br	
1	Beige wood shell	BL	BL	BL	BL	BL	NA
2	Silvery metal ring	BL	BL	BL	BL	--	NA
3	Silvery magnetic sheet	BL	BL	BL	IN	--	Cr <sup>6+</sup> : ND
4	Solder	BL	BL	BL	BL	--	NA
5	White fibrous wire	BL	BL	BL	BL	BL	NA
6	Coppery metal winding	BL	BL	BL	BL	--	NA
7	Dark grey magnetic sheet	BL	BL	BL	BL	--	NA
8	Transparent plastic adhesive sheet	BL	BL	BL	BL	BL	NA
9	Black sponge with adhesive	BL	BL	BL	BL	BL	NA
10	Yellow transparent plastic adhesive tape	BL	BL	BL	BL	BL	NA
11	White plastic shell(USB plug)	BL	BL	BL	BL	BL	NA
12	Silvery metal shell(USB plug)	BL	BL	BL	BL	--	NA
13	White plastic sheet(USB plug)	BL	BL	BL	BL	BL	NA
14	Silvery metal pin(USB plug)	BL	BL	BL	BL	--	NA
15	Transparent soft plastic cord anchorage	BL	BL	BL	BL	BL	NA
16	Silvery plastic film	BL	BL	BL	BL	BL	NA
17	Solder	BL	BL	BL	BL	--	NA
18	Chip diode	BL	BL	BL	BL	BL	NA
19	Chip resistor	BL	BL	BL	IN	BL	Cr <sup>6+</sup> : ND



Part No.	Part Description	Result of XRF					Result of Wet Chemical Testing (mg/kg)
		Cd	Pb	Hg	Cr	Br	
20	Chip resistor	BL	BL	BL	IN	BL	Cr <sup>6+</sup> : ND
21	Chip capacitor	BL	IN	BL	BL	BL	Pb : ND
22	Chip audion	BL	BL	BL	BL	BL	NA
23	Chip IC	BL	BL	BL	BL	BL	NA
24	Red varnished wire	BL	BL	BL	BL	BL	NA
25	Copperry varnished wire	BL	BL	BL	BL	BL	NA
26	White fibrous wire	BL	BL	BL	BL	BL	NA
27	Chip LED	BL	BL	BL	BL	BL	NA
28	Red capacitor	BL	BL	BL	BL	BL	NA
29	Chip IC	BL	BL	BL	BL	IN	PBBs : ND PBDEs : ND
30	White plastic wire covering	BL	BL	BL	BL	BL	NA
31	Green PCB	BL	BL	BL	BL	IN	PBBs : ND PBDEs : ND
32	Silvery metal screw	BL	BL	BL	BL	--	NA
33	Black plastic shell	BL	BL	BL	BL	IN	PBBs : ND PBDEs : ND
34	Black plastic wire covering	BL	BL	BL	BL	BL	NA
35	Black plastic shell	BL	BL	BL	BL	IN	PBBs : ND PBDEs : ND
36	White plastic shell	BL	BL	BL	BL	BL	NA
37	Black soft plastic gasket	BL	BL	BL	BL	BL	NA
38	White soft plastic gasket	BL	BL	BL	BL	BL	NA



Report No.: WTF22F09192785C

**Remark:**

- (1) Results are obtained by EDXRF for primary screening, and further chemical testing by ICP (for Cd, Pb, Hg), UV-VIS (for Cr<sup>6+</sup>) and GC-MS (for PBBs, PBDEs) is recommended to be performed, if the concentration exceeds the below warning value according to IEC 62321-3-1: 2013 (unit: mg/kg)

Element	Polymer	Metal	Composite Materials
Cd	$BL \leq (70-3\sigma) < IN < (130+3\sigma) \leq OL$	$BL \leq (70-3\sigma) < IN < (130+3\sigma) \leq OL$	$LOD < IN < (150+3\sigma) \leq OL$
Pb	$BL \leq (700-3\sigma) < IN < (1300+3\sigma) \leq OL$	$BL \leq (700-3\sigma) < IN < (1300+3\sigma) \leq OL$	$BL \leq (500-3\sigma) < IN < (1500+3\sigma) \leq OL$
Hg	$BL \leq (700-3\sigma) < IN < (1300+3\sigma) \leq OL$	$BL \leq (700-3\sigma) < IN < (1300+3\sigma) \leq OL$	$BL \leq (500-3\sigma) < IN < (1500+3\sigma) \leq OL$
Cr	$BL \leq (700-3\sigma) < IN$	$BL \leq (700-3\sigma) < IN$	$BL \leq (500-3\sigma) < IN$
Br	$BL \leq (300-3\sigma) < IN$	--	$BL \leq (250-3\sigma) < IN$

BL= Below Limit                      OL= Over Limit                      LOD = Limit of Detection                      -- = Not Regulated

- (2) "IN" expresses the inconclusive region, and further chemical testing to confirm whether it complies with the requirement of RoHS Directive.
- (3) The XRF screening test for RoHS elements – the reading may be different to the actual content in the sample be of non-uniformity composition.
- (4) mg / kg =milligram per kilogram=ppm,  $\mu\text{g}/\text{cm}^2$ = Micrograms per square centimetre.
- (5) ND = Not Detected or lower than limit of quantitation.
- (6) NA = Not Applicable, as the XRF screening test result was below the limit or as the XRF screening directly determine that test result was over the limit, it was not need to conduct the wet chemical testing.
- (7) LOQ = Limit of quantitation.

Test Items	Pb	Cd	Hg	Cr <sup>6+</sup>		PBB	PBDE
Units	mg/kg	mg/kg	mg/kg	mg/kg	$\mu\text{g}/\text{cm}^2$	mg/kg	mg/kg
LOQ	2	2	2	8	0.1	5	5

The LOQ for single compound of PBBs and PBDEs is 5mg/kg, LOQ of Cr<sup>6+</sup> for polymer and composite sample is 8mg/kg and LOQ of Cr<sup>6+</sup> for metal sample is 0.1 $\mu\text{g}/\text{cm}^2$ .

- (8) RoHS Requirement

Restricted Substances	Limits
Cadmium (Cd)	0.01% (100 mg/kg)
Lead (Pb)	0.1% (1000 mg/kg)
Mercury (Hg)	0.1% (1000 mg/kg)
Chromium (VI) (Cr <sup>6+</sup> )	0.1% (1000 mg/kg)
Polybrominated Biphenyls (PBBs)	0.1% (1000 mg/kg)
Polybrominated Diphenyl Ethers (PBDEs)	0.1% (1000 mg/kg)



Report No.: WTF22F09192785C

(9) According to IEC 62321-7-1:2015, determined of Cr<sup>6+</sup> on metal sample by boiling water extraction test method, and result is shown as Positive/Negative.

Boiling water extraction:

Negative = Absence of Cr<sup>6+</sup> coating, the detected concentration in boiling water extraction solution is less than 0.10ug/cm<sup>2</sup>.

Positive = Presence of Cr<sup>6+</sup> coating, the detected concentration in boiling water extraction solution is greater than 0.13ug/cm<sup>2</sup>.

Information on storage conditions and production date of the tested sample is unavailable and thus Cr<sup>6+</sup> results represent status of the sample at the time of testing.

(10) Abbreviation:

“Pb” denotes Lead, “Cd” denotes Cadmium, “Hg” denotes Mercury, “Cr” denotes Chromium, “Cr (VI)” denotes Hexavalent Chromium, “Br” denotes Bromine, “PBBs” denotes Total Polybrominated Biphenyls, “PBDEs” denotes Total Polybrominated Diphenyl Ethers.

## 2. Phthalates:

Serial No.	Part No.	Result (mg/kg)			
		DBP	BBP	DEHP	DIBP
T01	1	ND	ND	ND	ND
T02	2	--	--	--	--
T03	3	--	--	--	--
T04	4	--	--	--	--
T05	5	ND	ND	ND	ND
T06	6	--	--	--	--
T07	7	--	--	--	--
T08	8	ND	ND	ND	ND
T09	9	ND	ND	ND	ND
T10	10	ND	ND	ND	ND
T11	11+13+33+35+36 <sup>Δ</sup>	ND	ND	ND	ND
T12	12	--	--	--	--
T13	14	--	--	--	--
T14	15	ND	ND	ND	ND
T15	16	ND	ND	ND	ND
T16	17	--	--	--	--
T17	18+19+20+21+22 <sup>Δ</sup>	ND	ND	ND	ND
T18	23+24+25+27+28 <sup>Δ</sup>	ND	ND	ND	ND
T19	26	ND	ND	ND	ND
T20	29+31 <sup>Δ</sup>	ND	ND	ND	ND
T21	30	ND	ND	ND	ND
T22	32	--	--	--	--
T23	34	ND	ND	ND	ND
T24	37	ND	ND	ND	ND
T25	38	ND	ND	ND	ND



Report No.: WTF22F09192785C

**Note:**

- (1) mg/kg = milligram per kilogram= ppm
- (2) ND = Not Detected or lower than limit of quantitation.
- (3) -- = Not Regulated.
- (4) LOQ = Limit of quantitation.

Test Items	DBP	BBP	DEHP	DIBP
Units	mg/kg	mg/kg	mg/kg	mg/kg
LOQ	50	50	50	50

- (5) Abbreviation:  
 “DBP” denotes Dibutyl phthalate, “BBP” denotes Benzyl butyl phthalate (BBP), “DEHP” denotes Bis(2-ethylhexyl)-phthalate, “DIBP” denotes Diisobutyl phthalate, “PHT” denotes Phthalates.

- (6) RoHS requirement


Restricted Substances	Limits
Dibutyl phthalate (DBP)	0.1% (1000 mg/kg)
Benzyl butyl phthalate (BBP)	0.1% (1000 mg/kg)
Di(2-ethylhexyl) phthalate (DEHP)	0.1% (1000 mg/kg)
Di-iso-butyl phthalate (DIBP)	0.1% (1000 mg/kg)

- (7) “△”= As client’s requirement, the testing was conducted based on mixed components. Results are calculated by the minimum weight of mixed components.

# WALTEK




**Measurement Flowchart:**





Photograph(s) of parts tested:





Remarks:

1. The results shown in this test report refer only to the sample(s) tested;
2. This test report cannot be reproduced, except in full, without prior written permission of the company;
3. The report would be invalid without specific stamp of test institute and the signatures of compiler and approver;
4. The Applicant name and Address, the sample(s) and sample information was/were provided by the applicant who should be responsible for the authenticity which Waltek hasn't verified;
5. If the report is not stamped with the accreditation recognized seal, it will only be used for scientific research, education, and internal quality control activities, and is not used for the purpose of issuing supporting data to the society.
6. The sample material information (Model No. information) is provided by client, not verified by test laboratory. The samples of reference Model No. are not tested. Test laboratory not responsible for the accuracy, appropriateness, completeness and authenticity of the information provided by client.

===== End of Report =====